



Physical Properties:

RESULTS							
DESCRIPTION	COATER	PANEL #	TEST	EDGE	SCRIBE	FIELD	BORE
XT3G41329		1	CCH	0mm	0mm	10	10
XT3G41329		2	SS	1mm	1mm	10	10
XT3G41329		3	HUMIDITY	0mm	0mm	10	10
XG3G41766		1	CCH	0mm	0mm	10	10
XG3G41766		2	SS	1mm	1mm	10	10
XG3G41766		3	HUMIDITY	0mm	0mm	10	10
CAS 1050		1	CCH	0mm	0mm	10	10
CAS 1050		2	SS	13mm	1mm	10	4F
CAS 1050		3	HUMIDITY	0mm	0mm	10	10
XG1Y44633		1 of SET 1	CCH	0mm	0mm	10	10
XG1Y44633		2 of SET 1	SS	1mm	0mm	10	10
XG1Y44633		3 of SET 1	HUMIDITY	0mm	0mm	10	10
XG1Y44633		1 of SET 2	CCH	0mm	0mm	10	10
XG1Y44633		2 of SET 2	SS	1mm	0mm	10	10
XG1Y44633		3 of SET 2	HUMIDITY	0mm	0mm	10	10
PW2R29875		1	CCH	0mm	0mm	10	10
PW2R29875		2	SS	2mm	0mm	10	10


CAS1050 / 1402W GALV




PW2R29875 / 1402W HDG




XT3G41329 / 1402W HDG



XG3G41766 / 1421 HDG



XG1Y44633 / 1421 HDG SET 1



XG1Y44633 / 1421 HDG SET 2

